

Product Data Sheet

No. 1710 - 6/08

STRIPING PAINT AEROSOL & BULK LIQUID

Aerosol VOC <66% ; CARB MIR \leq 1.20 Ground Traffic; Bulk VOC 505 g/l

PRODUCT NUMBERS: 710 - Traffic White
720 - Traffic Yellow
730 - Traffic Red
740 - Traffic Orange
750 - Traffic Blue
760 - Traffic Green
770 - Traffic Black

Product number plus letter designation is as follows:
G = 1 one gallon can; F=1 five-gallon pail; D = 55-gallon drum

I. GENERAL DESCRIPTION

Description: Uniquely formulated to adhere to a variety of surfaces, especially asphalt and concrete. Aervoe Striping Paint formulas offer excellent resistance to traffic and oil. Application is via a line striping machine, which will allow the line width to be adjusted from 2 to 4 inch.

Benefits: Aervoe Striping Paint is versatile and economical for small- to- medium sizes jobs. This product is cost effective for achieving professional results with no special operator training required. Use of Aervoe aerosol Striping Paint eliminates paint waste and clean-up. For large applications, the bulk striping paint is most economical. All colors are lead-free.

Uses: This paint may be used for line striping on parking lots, warehouses, school yards, factory safety aisles, tennis courts, baseball fields, tracks and other applications where separations and storage areas are needed.

Application: Aervoe Striping Paint is intended for use with Aervoe's Striping equipment; test other applicators for compatibility. Apply to clean, dry, and oil-free surfaces only. The aerosol Striping Paint should be used in the #798 Econo Striper or the #800 Vers-A-Striper. For stenciling and touch up, use the #745 Striping Stick.

Directions: Shake can vigorously for at least one minute after rattle of agitator ball is heard. Use only when can temperature is between 65° and 85°F (18° and 29°C). Can temperatures above and below this range may cause fuzzy edges or thin coverage. Before storing partially used cans, clear spray tip by holding can in upright position and pressing tip to one side, away from face, for 2-3 seconds. Aervoe bulk Striping Paint should be stirred thoroughly before use. For best results, strain to remove oversized material and any other contaminants. Thin paint to proper viscosity.

Limitations: Please refer to the Material Safety Data Sheets for specific information on material hazards, etc. The aerosol product is designed to spray upside down only, and will not deliver paint if the tip is activated while being pointed above horizontal. Heavy applications on turf surfaces will result in grass root damage, therefore, we recommend using Aervoe's water-based Athletic Striping Paint. Allow new asphalt or seal coated surfaces to cure 4 to 7 days before applying Striping Paint, as the asphalt will bleed through white paint and turn it brown. Should a tip become clogged due to storage in the machine, we have supplied 15 extra per case.

Packaging:

Aerosol:	Cans (211 x 713)	18 oz. net wt.	(510 grams)	18.8 fl. oz.	(556 ml)
	Case - 12 cans/case	18 lbs.	(8.2 kg)	.55 CF	(.016 CM)
Liquid Bulk:					
	1 case of 2 gallons	23 lbs.	(10.4 kg)	.13 CF	(.004 CM)
	5-gallon pail (mt. rd.)	54 lbs.	(24.5kg)	1.2 CF	(.034 CM)
	55-gallon drum (mt. rd.)	535 lbs.	(243.2 kg)	8.5 CF	(.24 CM)



AERVOE INDUSTRIES INCORPORATED

P.O. Box 485, Gardnerville NV 89410 • 800-227-0196 Order Desk • 800-921-0065 Order Fax • mailbox@aervoe.com • www.aervoe.com

II. CHARACTERISTICS AND PROPERTIES Average for all colors

Specifications: Formulated to approximate color requirements of Fed. Reg. Title 49 of D.O.T.

Appearance:	Aerosol	Bulk
Gloss at 60°	25-50	10-35
Class	Semi Gloss	Semi Gloss
Coverage:	Aerosol	Bulk
Theoretical—at 1/2 mil dry (2 inch wide stripe)	137 Linear ft./can	568 sq. ft./gal
Practical—at 1mil dry (2 inch wide stripe)	69 Linear ft./can.....	284 sq. ft./gal
Drying Schedule: (At 77°F [25°C], 50% Humidity at 1 mil, dry)		
To touch	20 min.....	20 min.
To handle	60 min.....	30 min.
Full cure	8 hrs.....	8 hrs.
To recoat	30 min.....	30 min.
Performance and Chemical Properties:		
Weight per gallon	6.8 lbs.....	9.9 lbs.
Specific gravity	0.82	1.19
Viscosity	Not applicable.....	55-70 KU
Flammability: Label marking	Extremely flammable.....	Extremely Flammable
Flash point.....	<22°F (-30°C).....	<73°F (23°C)
Operating temperature range.....	65° to 85°F (18° to 29°C)	60° to 80°F (16° to 27°C)
Percent solids by weight	22%	62%
Percent solids by volume	10%	35%
Percent pigment by volume	4.5%	27%
Volatile Organic Compound level.....	<66%	<505 grams per liter
CARB MIR.....	≤1.20% Ground Traffic.....	N/A
Interior durability	Excellent.....	Excellent
Exterior durability	Very Good	Very Good
Temperature resistance	N/A.....	N/A
Color fastness	Good.....	Good
Adhesion	Good.....	Good
Mineral Spirits resistance.....	Good.....	Good
Gasoline resistance	Poor.....	Poor
Motor oil resistance.....	Excellent.....	Excellent
Food contact rating	Not applicable.....	Not applicable
Base Materials:		
Resin system	Acrylic VT Alkyd.....	Acrylic VT Alkyd
Solvents (top two)	Water/Hexane	VM&P Naptha/Acetone
Propellant system	Hydrocarbon.....	Not applicable

III. SHIPPING, STORAGE AND HEALTH

IMDG number	1950	1263
D.O.T. container spec	2P	1A1, 1A2
D.O.T. shipping description.....	Consumer commodity	Paint Related Material
Warehouse storage level number	NFPA 30B Level 2	Flammable liquid class 1-B
Hazardous class (CFR-49)	ORM-D.....	Flammable liquid
Storage temperature	32° to 120°F (0° to 49°C)	32° to 120°F (0° to 49°C)
Shelf life	12 to 24 months.....	12 to 24 months
HMIS ratings		
Health	2	2
Fire	4	3
Reactivity	1	1

IV. MISCELLANEOUS

Contains no Ozone Depleting Substances (O.D.S.).

V. WARRANTY

The statements made herein, on labels, product bulletins or by any of our employees or agents concerning this material are given for information only. Any liability whatsoever of Aervoe Industries Inc. to the user of the product, is limited to replacement of the product or purchase price refunded.

No. 1710-6/08